

TECHNICAL DATA SHEET

Product: Alreflex Platinum Dry Lining Board
Issue Number: 003
Issue Date: May 2025

Product Information

Description

Alreflex Platinum is a rigid, graphite-injected, expanded polystyrene board; laminated with a single layer of polythene bubble sheet, faced with low-emissive aluminium foil protected by a thin NC coating. Alreflex Platinum can be sealed with Thermal Economics Alu Tape to form a vapour barrier.

Application

Dry lining insulation for use in wall constructions.

Appearance & Packaging

Supplied in boards, stock sizes (*other sizes available on request*):

0.6m x 1.2m

Physical Properties

Thickness	: 25mm – 100mm	(<i>other sizes available on request</i>)
Density	: 13 – 15 kg/m ³	(BS EN 13163)
Bending Strength	: 100 kPa	(BS EN 13163)
Compressive Strength	: 13 kPa (@ 1% compression)	(BS EN 13163)
Compressive Stress	: 60 kPa (@ 10% deformation)	(BS EN 13163)
Water Vapour Resistance of bubble/foil	: 150MN · s/g	(BBA Cert No. 93/2861)
Water Vapour Resistance of EPS	: 60MN · s/g	(BBA Cert No. 93/2861)
Water Vapour Permeability of EPS	: 0.018 – 0.036 mg/Pa · h · m	
Vapour Diffusion Factor (μ)	: 20 – 40	(BS EN 13163)

If you require any further technical information please contact our Technical Department on 01582 544255.

Thermal Performance

Foil Emissivity	: 0.05	(BBA Cert No. 93/2861)
Resistance of (min) 20mm residual cavity	: $0.67\text{m}^2 \cdot \text{K/W}$	(BBA Cert No. 93/2861)
Resistance of bubble/foil	: $0.10\text{m}^2 \cdot \text{K/W}$	(BBA Cert No. 93/2861)
Thermal Conductivity of EPS (λ)	: $0.030 \text{ W/m} \cdot \text{K}$	(BS EN 13163)

Environmental Data

BRE Green Guide Rating : A+

Global Warming Potential : < 5

Ozone Depletion Potential : 0